



PRODUCT'S CARD

SANWIA M-750

Usage



Coating - PVC	100%
Backing - PES	100%
Weight [g/m ²]	560±60
Thickness [mm]	0,8 ± 0,2
Tensile strength [daN/5cm] Method 2 along / across	≥ 35 ≥ 15
Flame retardancy	+
Flame retardancy	+
Flame retardancy	PN EN 1021-1 PN EN 1021-2



PRODUCT'S CARD

SANWIA M-750



REACH



OEKO-TEX



Phtalates free



Fireproof